

Your composition:

6 mm Stopsol Classic Bronze pos.1 - 12 mm Air 100% - 6 mm Planibel Clearlite

Personal notes:

LIGHT

Transmission	19
Reflection	34

ENERGY

Solar factor	31
Reflection	29



LIGHT PROPERTIES (EN 410)

EN 410

Light Transmission - τ_v (%)	19
Light Reflection - ρ_v (%)	34
Internal light reflection - ρ_{vi} (%)	17
Colour Rendering - RD65 - Ra (%)	83

ENERGY PROPERTIES

EN 410 ISO 9050

Solar factor - g (%)	31	33
Energy Reflection - ρ_e (%)	29	28
Direct Energy Transmission - τ_e (%)	25	26
Solar abs. Glass 1 - α_e (%)	44	44
Solar abs. Glass 2 - α_e (%)	2	2
Total Energy absorption - α_e (%)	46	46
Shading coefficient - SC	0.36	0.38
UV Transmission - UV (%)	4	
Selectivity	0.61	0.58

OTHER PROPERTIES

Resistance to fire - EN 13501-2	NPD
Reaction to fire - EN 13501-1	NPD
Bullet Resistance - EN 1063	NPD
Burglar Resistance - EN 356	NPD
Pendulum body impact resistance - EN 12600	NPD / NPD

ACOUSTIC PROPERTIES

Direct airborne sound insulation(R_w (C;Ctr) - EN 12758) - dB	31 (-1; -3) ⁽¹⁾
--	----------------------------

THICKNESS AND WEIGHT

Nominal thickness (mm)	24
Weight (kg/m ²)	30

THERMAL PROPERTIES (EN 673)	EN 673
Ug-Value - W/(m ² .K)	2.8

The data are calculated using spectral measurements that are conform to standards EN 410, ISO 9050 (1990) and WIS/WINDAT. The Ug-value (formerly k-value) is calculated according to standard EN 673. The emissivity measurement complies with standards EN 673 (Annex A) and EN 12898.

This document is no evaluation of the risk of glass breakage due to thermal stress. For tempered glass: the risk of spontaneous breakage due to Nickel-Sulfide is not covered by AGC Glass Europe. The Heat Soak Test is available on request.

Specifications, technical and other data are based on information available at the time of preparation of this document and are subject to change without notice. AGC Glass Europe can not be held responsible for any deviation between the data introduced and the conditions on site. This document is only informative, in no way it implies an acceptance of the order by AGC Glass Europe.

While the AGC GlassConfigurator allows for accurate measurement of the above performances, the AGC GlassConfigurator does not create any supplementary liability on the part of AGC with regard to the AGC products delivered to customers. AGC's liability remains limited to the AGC products manufactured and delivered by AGC only.

The user of the AGC GlassConfigurator undertakes to provide clear and comprehensive information and to refrain from any misleading commercial practice which would be likely to deceive the customers as to the manufacturer of the products it purchases.

The user of the AGC GlassConfigurator undertakes to indemnify and hold harmless AGC from and against any and all claims, costs and damages arising out of, or relating to improper / misleading use of the AGC GlassConfigurator.

See also conditions of use.

⁽¹⁾These sound reduction indexes correspond to glazings which are 1,23 by 1,48m according to EN ISO 10140-3 and are tested in laboratory conditions. In-situ performances may vary according to the effective glazing dimensions, frame system, noise sources etc. The accuracy of the given indexes is not better than +/- 1dB.

⁽²⁾These sound reduction indexes are estimated (no test).They correspond to glazings which are 1,23m. by 1,48 m. In-situ performances may vary according to the effective glazing dimensions, frame system, noise sources etc. The accuracy of the given indexes is +/- 2dB.